



TEST REPORT

1. NO : CT23-020313E

2. Client

○ Name : ALCODAEA CO.,LTD

○ Address : 276, Daechong-ro, Sanseong-myeon, Eumseong-gun, Chungcheongbuk-do, Republic of Korea

3. Date of Test : 2023.02.22 ~ 2023.03.10

4. Use of Report : Quality Control

5. Test Sample : ALUMINIUM EMBO PANEL(4T)

6. Test Method

(1) KS M ISO 15184:2012

(2) KS F 4737:2019

(3) KS D 8303:2009

7. Test Results

1) ALUMINIUM EMBO PANEL(4T)

Test Item(s)	Unit	Test Method	Test Results	Remark	Loc.
Pencil hardness	-	(1)	4H	-	A
Stain resistance - crayon(red)	grade	(2)	5		
Stain resistance - crayon(red)	grade	(2)	5		
Stain resistance - crayon(red)	grade	(2)	5		
Cross-cut test	-	(3)	No peeling of the coating (100/100)		

※ Location

A : 85, Dambang-ro, Namdong-gu, Incheon, Korea

----- End of Report -----




Affirmation	Tested By Name : Kim Eung Gu	Technical Manager Name : Shin Kwon II
This report is not accredited by KOLAS and KS Q ISO/IEC 17025. Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).		

2023.03.10

Korea Conformity Laboratories

President Jo, Yung Tae

Result Inquiry : 40, Yeongudangi-ro, Ohchang-Eup, Cheongwon-Gu, Cheongju-si, Chungbuk, Korea (82-43-718-9054)





TEST REPORT

1. NO : CT23-020316E

2. Client

○ Name : ALCODAEA CO.,LTD

○ Address : 276, Daechong-ro, Sanseong-myeon, Eumseong-gun, Chungcheongbuk-do, Republic of Korea

3. Date of Test : 2023.02.22 ~ 2023.03.16

4. Use of Report : Quality Control

5. Test Sample : ALUMINIUM EMBO PANEL(4T)

6. Test Method

(1) KS F 4737:2019

7. Test Results

1) ALUMINIUM EMBO PANEL(4T)

Test Item(s)	Unit	Test Method	Test Results	Remark	Loc.
Peeling and Adhesive Load	N/25 mm	(1)	85.9	(23 ± 2) °C. (50 ± 5) % R.H.	A

※ Location

A : 628, Sorae-ro, Namdong-gu, Incheon, 21594, Korea

----- End of Report -----

Affirmation	Tested By Name : Kim Eung Gu	Technical Manager Name : Shin Kwon Il
-------------	---------------------------------	--

This report is not accredited by KOLAS and KS Q ISO/IEC 17025.

Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).

2023.03.16

Korea Conformity Laboratories

President Jo, Yung Tae

Result Inquiry : 40, Yeongudangi-ro, Ohchang-Eup, Cheongwon-Gu, Cheongju-si, Chungbuk, Korea (82-43-718-9054)

